

Summary Letter Reference: CT/339818 Issue 2

Data: 15th June 2015

Prepared for:

Rudolf Hensel GmbH

Lauenburger Landstr 11,
D-21039 Bornsen,
Germany

Summary letter for determining the contribution of protection system to the fire resistance of concrete beam members

To ensure the reinforced concrete beams in buildings have the required fire resistance ability, the beam thickness and the thickness of concrete cover to the rebars must not be less than a certain level in accordance with EN 1992-1 Part 2. In the cases where the thickness of beam or concrete cover in existing reinforced concrete beam is deficient, it is possible to improve the fire resistance by applying intumescent paint system to the beam. This letter presents a summary of the assessment of an intumescent coating system known as HENSOMASTIK B 3000 to fire protect structural concrete beams in accordance with EN 13381-3:2015 for periods of fire resistance up to 120 minutes.

In accordance with section 5.6.3 in BS EN 1992-1 part 2, the required minimum beam thickness of reinforced concrete solid beams with a width of 160 mm are 15 mm (For R 30), 30 mm (For R 60), 40 mm (For R 90) and 55 mm (For R 120). Generally when the overall beam thickness is equal or greater than those values, the load bearing capacity of the beam is deemed to be satisfied; while when the concrete cover over the rebar is deficient it is necessary to improve the protection to meet the appropriate load bearing capacity.

The required dry film thickness (DFT) of HENSOMASTIK B 3000 to remedy the concrete cover deficiency is summarised in the tables below using linear interpolation avoiding non-conservative predictions against depth inside concrete beam along vertical axis at which steel reinforcing bars are positioned, with a predefined failure temperature of 500°C of the reinforcing bars. It is understood that the temperature distribution (where rebar location is concerned) can be affected by the actual thickness of the reinforced concrete slab, however this variation is considered limited given the overall insulation performance will be met by the minimum required beam thickness. Therefore this variation has not been taken into account in this letter.

The data in the tables is based on the tests reports WF nos. 330435 and 332031 and assessment report 339818, with the following limits of applicability.

- 1) The concrete cover prior to application of protection should meet the requirements in BS EN 1992-1 Part 1.
- 2) Consult Rudolf Hensel for the requirements of preparation of the concrete base prior to application of HENSOMASTIK B 3000.
- 3) The load ratio of the beam in fire condition should be not greater than 0.6
- 4) The results presented in this letter are based on the fire protection system tested in horizontal orientation on concrete beams. Therefore, following the EN 13381-3:2015 Clause 15, the results are applicable to all beams and columns, in use in both horizontal and vertical orientation
- 5) Other limits of applicability in EN 13381-3:2015 (e.g. Clause 15)

Table 1. Required 'HENSOMASTIK B 3000' dry film thickness to improve fire resistance of the reinforced concrete beam for the period of 30 minutes.

30 minutes fire resistance period	
Depth of the reinforcing bar inside concrete beam along vertical axis, mm	Required 'HENSOMASTIK B 3000' dry film thickness for the 500°C design reinforcing bar temperature, mm
< 15	1.313
≥ 15	No protection required

Table 2. Required 'HENSOMASTIK B 3000' dry film thickness to improve fire resistance of the reinforced concrete beam for the period of 60 minutes.

60 minute fire resistance period	
Depth of the reinforcing bar inside concrete beam along vertical axis, mm	Required 'HENSOMASTIK B 3000' dry film thickness for the 500°C design reinforcing bar temperature, mm
8	3.435
9	3.242
10	3.049
15	2.085
18	1.506
Between 19 and 30	1.313
≥ 30	No protection required

Table 3. Required 'HENSOMASTIK B 3000' dry film thickness to improve fire resistance of the reinforced concrete beam for the period of 90 minutes.

90minute fire resistance period	
Depth of the reinforcing bar inside concrete beam along vertical axis, mm	Required 'HENSOMASTIK B 3000' dry film thickness for the 500°C design reinforcing bar temperature, mm
28	3.435
30	3.049
32	2.663
34	2.278
36	1.892
38	1.506
39	1.313
≥ 40	No protection required

Table 4. Required 'HENSOMASTIK B 3000' dry film thickness to improve fire resistance of the reinforced concrete beam for the period of 120 minutes.

120 minute fire resistance period	
Depth of the reinforcing bar inside concrete beam along vertical axis, mm	Required 'HENSOMASTIK B 3000' dry film thickness for the 500°C design reinforcing bar temperature, mm
41	3.435
43	3.109
45	2.782
47	2.456
49	2.129
51	1.803
53	1.476
54	1.313
≥ 55	No protection required

We trust that the information presented in this letter will be useful to you.

Yours sincerely



Dmitrij Podolski

Senior Certification Engineer
For and behalf of
Exova Warringtonfire

24th August 2018: Issue 2 – editorial changes and addition of the statement allowing application of results to columns.

This assessment represents our opinion as to the performance likely to be demonstrated on a test in accordance with prEN 13381-3:2012, on the basis of the evidence referred to above. We express no opinion as to whether that evidence, and/or this assessment, would be regarded by any Building Control authority as sufficient for that or any other purpose. This assessment is provided to the client for its own purposes and we cannot opine on whether it will be accepted by Building Control authorities or any other third parties for any purpose.

This copy has been produced from a .pdf format electronic file that has been provided by Exova Warringtonfire to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of Exova Warringtonfire. The pdf copy supplied is the sole authentic version of this document. All pdf versions of this report bear authentic signatures of the responsible Exova Warringtonfire staff.